

The German spirit of quality since 1854



**SiLibeads** <sup>AIR</sup>®

...light and strong products



## HOLLOW GLASS BEADS

Examples of Applications:

- Filling material for the modification of the physical properties of thermoplastics and duroplastics
- Filling material for the reduction of weight in composite materials as lightweight concretes or cements
- As a thermal insulator in thermal insulating coatings (also for the modification of the physical properties of the coatings)
- Effect material for decorative effects in wall paints and further technical applications

Standard Sizes –special diameters available by request			
Article	Patikel sizes D10 / D50 / D90	Bulk density	Crushing strength
8015	30 µm / 70 µm / 110 µm	0.10 g/cm <sup>3</sup>	2 Mpa
8020	32 µm / 68 µm / 106 µm	0.12 g/cm <sup>3</sup>	4 Mpa
8025	30 µm / 65 µm / 100 µm	0.15 g/cm <sup>3</sup>	5 Mpa
8032	30 µm / 56 µm / 74 µm	0.19 g/cm <sup>3</sup>	14 Mpa
8038	20 µm / 50 µm / 80 µm	0.21 g/cm <sup>3</sup>	36 Mpa
8040	20 µm / 45 µm / 70 µm	0.23 g/cm <sup>3</sup>	28 Mpa
8046	22 µm / 45 µm / 65 µm	0.26 g/cm <sup>3</sup>	41 Mpa
8060	18 µm / 40 µm / 60 µm	0.35 g/cm <sup>3</sup>	55 Mpa
8070	15 µm / 30 µm / 40 µm	0.42 g/cm <sup>3</sup>	124 Mpa
8082	18 µm / 40 µm / 60 µm	0.35 g/cm <sup>3</sup>	82 Mpa

Technical Data	
Size Range:	Between 10 and 150 µm
Density (g/cm <sup>3</sup> ):	0.15 – 0.70
Bulk Density (g/cm <sup>3</sup> ):	0.10 – 0.42
Rate of Floatage (%):	90 - 95
pH-Value:	8.0 – 9.5
Softening point:	625 °C
Appearance:	colorless rigid spheres; white powder in bulk

Chemical Analysis	Weight
Silicon dioxide SiO <sub>2</sub>	72.50%
Boric oxide B <sub>2</sub> O <sub>3</sub>	11.50%
Calcium oxide CaO	10.00%
Sodium oxide Na <sub>2</sub> O	5.00 %
further	1.00 %

For more technical information please contact:

Dr. Alexander Wölfel  
alexander.woelfel@sigmund-lindner.com  
Phone +49 9277 994 52



**SiLibeads** <sup>AIR</sup>®

9001-17-F\_en SiLibeads SOLID/AIR Edition 1.0/ February 2019